

CONTRIPON DPG

Humidity regulator

Chemical composition

Polyalcohol

Aspect:	liquid, colourless
Active matter:	approx. 100 %
Ionogenicity:	anionic
pH (10%):	approx. 6 - 7
Solubility:	soluble in water
Storage stability:	The product can be stored up to one year in the original sealed packing. The product may separate under very cold or too warm storage conditions. Therefore CONTRIPON DPG should be mixed by stirring, pump circulation or any other suitable method before use.

Properties

With CONTRIPON DPG produced leathers achieve a constant humidity, even if the leathers were overdried or stored.

CONTRIPON DPG also reduces the possibility of grain cracks and is especially recommended for the use on

- upholstery leathers
- all kinds of nappa leathers

CONTRIPON DPG is suitable for automotive leather.

Application

CONTRIPON DPG is added together with the main fatliquoring agents. Normal fatliquoring agents are mixed with CONTRIPON DPG and then emulsified. An application of 0.5 - 2.0 % CONTRIPON DPG, referring to the shaved weight, is recommended.

The above results have been obtained from trials in our laboratory and plant. In the light of changing conditions they can serve only as a guide and are therefore offered without obligation. We ask you to observe the possible rights of third parties.

Stand: 13. January 2012